

# TRAVERTINO

---



---

Test	Test method	Value
Bulk gravity	UNE-22182	2447 kg/m <sup>3</sup>
Absorption	UNE-22182	1.00%
Compressive strength	UNE-22185	100 MPa
Flexure strength	UNE-22186	15 MPa
Abrasion resistance	UNE-22183	25 mm
Slip resistance	UNE-14231	58 USRV